

LAGARTERA

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9001 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4,699	+4,699	0,30	0,30
-4+6	-4,699+3,327	3,954	1,02	1,32
-6+8	-3,327+2,362	2,803	1,56	2,88
-8+10	-2,362+1,651	1,972	4,83	7,71
-10+14	-1,651+1,168	1,389	6,09	13,80
-14+20	-1,168+0,833	0,986	8,66	22,46
-20+28	-0,833+0,589	0,700	8,01	30,47
-28+35	-0,589+0,417	0,495	16,53	46,99
-35+48	-0,417+0,295	0,350	10,13	57,12
-48+65	-0,295+0,208	0,247	7,80	64,92
-65+100	-0,208+0,147	0,174	5,00	69,92
-100+150	-0,147+0,104	0,123	6,33	76,25
-150+200	-0,104+0,074	0,087	5,04	81,30
-200+270	-0,074+0,053	0,062	5,02	86,32
-270+400	-0,053+0,038	0,044	4,28	90,60
-400	-0,038	-0,038	9,40	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9007

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4,699	+4,699	0,94	0,94
-4+6	-4,699+3,327	3,954	1,43	2,38
-6+8	-3,327+2,362	2,803	2,11	4,48
-8+10	-2,362+1,651	1,972	7,64	12,13
-10+14	-1,651+1,168	1,389	10,54	22,66
-14+20	-1,168+0,833	0,986	15,66	38,32
-20+28	-0,833+0,589	0,700	13,64	51,96
-28+35	-0,589+0,417	0,495	13,52	65,48
-35+48	-0,417+0,295	0,350	4,29	69,77
-48+65	-0,295+0,208	0,247	4,23	74,00
-65+100	-0,208+0,147	0,174	3,76	77,76
-100+150	-0,147+0,104	0,123	4,11	81,87
-150+200	-0,104+0,074	0,087	2,95	84,82
-200+270	-0,074+0,053	0,062	2,93	87,75
-270+400	-0,053+0,038	0,044	2,54	90,29
-400	-0,038	-0,038	9,71	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9008

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4,699	+4,699	0,00	0,00
-4+6	-4,699+3,327	3,954	1,77	1,77
-6+8	-3,327+2,362	2,803	4,46	6,22
-8+10	-2,362+1,651	1,972	14,85	21,07
-10+14	-1,651+1,168	1,389	13,97	35,04
-14+20	-1,168+0,833	0,986	12,76	47,81
-20+28	-0,833+0,589	0,700	8,96	56,76
-28+35	-0,589+0,417	0,495	8,50	65,26
-35+48	-0,417+0,295	0,350	2,91	68,17
-48+65	-0,295+0,208	0,247	3,48	71,65
-65+100	-0,208+0,147	0,174	2,46	74,11
-100+150	-0,147+0,104	0,123	2,48	76,59
-150+200	-0,104+0,074	0,087	1,89	78,48
-200+270	-0,074+0,053	0,062	1,86	80,34
-270+400	-0,053+0,038	0,044	1,44	81,78
-400	-0,038	-0,038	18,22	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9012 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4,699	+4,699	1,89	1,89
-4+6	-4,699+3,327	3,954	4,42	6,32
-6+8	-3,327+2,362	2,803	4,15	10,47
-8+10	-2,362+1,651	1,972	12,02	22,49
-10+14	-1,651+1,168	1,389	14,07	36,56
-14+20	-1,168+0,833	0,986	17,72	54,28
-20+28	-0,833+0,589	0,700	14,87	69,15
-28+35	-0,589+0,417	0,495	10,84	79,99
-35+48	-0,417+0,295	0,350	2,16	82,16
-48+65	-0,295+0,208	0,247	2,95	85,11
-65+100	-0,208+0,147	0,174	2,21	87,32
-100+150	-0,147+0,104	0,123	2,27	89,59
-150+200	-0,104+0,074	0,087	1,46	91,05
-200+270	-0,074+0,053	0,062	1,29	92,34
-270+400	-0,053+0,038	0,044	1,01	93,35
-400	-0,038	-0,038	6,65	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9013 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4.699	+4.699	0.00	0.00
-4+6	-4.699+3.327	3.954	0.00	0.00
-6+8	-3.327+2.362	2.803	0.00	0.00
-8+10	-2.362+1.651	1.972	0.00	0.00
-10+14	-1.651+1.168	1.389	7.95	7.95
-14+20	-1.168+0.833	0.986	8.97	16.92
-20+28	-0.833+0.589	0.700	13.06	29.98
-28+35	-0.589+0.417	0.495	36.94	66.92
-35+48	-0.417+0.295	0.350	12.47	79.39
-48+65	-0.295+0.208	0.247	5.22	84.61
-65+100	-0.208+0.147	0.174	3.68	88.29
-100+150	-0.147+0.104	0.123	3.43	91.72
-150+200	-0.104+0.074	0.087	1.93	93.65
-200+270	-0.074+0.053	0.062	1.53	95.18
-270+400	-0.053+0.038	0.044	0.95	96.13
-400	-0.038	-0.038	3.87	100.00
TOTAL			100.00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9014 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4,699	+4,699	2,94	2,94
-4+6	-4,699+3,327	3,954	8,52	11,45
-6+8	-3,327+2,362	2,803	6,24	17,69
-8+10	-2,362+1,651	1,972	9,24	26,93
-10+14	-1,651+1,168	1,389	8,30	35,24
-14+20	-1,168+0,833	0,986	9,79	45,03
-20+28	-0,833+0,589	0,700	8,99	54,02
-28+35	-0,589+0,417	0,495	13,96	67,97
-35+48	-0,417+0,295	0,350	7,06	75,03
-48+65	-0,295+0,208	0,247	6,72	81,76
-65+100	-0,208+0,147	0,174	3,95	85,70
-100+150	-0,147+0,104	0,123	3,55	89,26
-150+200	-0,104+0,074	0,087	2,04	91,30
-200+270	-0,074+0,053	0,062	2,13	93,43
-270+400	-0,053+0,038	0,044	1,20	94,63
-400	-0,038	-0,038	5,37	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9015 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4.699	+4.699	0.00	0.00
-4+6	-4.699+3.327	3.954	2.66	2.66
-6+8	-3.327+2.362	2.803	3.22	5.88
-8+10	-2.362+1.651	1.972	11.43	17.32
-10+14	-1.651+1.168	1.389	11.44	28.76
-14+20	-1.168+0.833	0.986	13.23	41.98
-20+28	-0.833+0.589	0.700	8.26	50.24
-28+35	-0.589+0.417	0.495	14.34	64.58
-35+48	-0.417+0.295	0.350	6.14	70.72
-48+65	-0.295+0.208	0.247	6.04	76.77
-65+100	-0.208+0.147	0.174	4.38	81.14
-100+150	-0.147+0.104	0.123	4.24	85.38
-150+200	-0.104+0.074	0.087	2.77	88.15
-200+270	-0.074+0.053	0.062	2.49	90.64
-270+400	-0.053+0.038	0.044	1.91	92.55
-400	-0.038	-0.038	7.45	100.00
TOTAL			100.00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9016 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4.699	+4.699	0,00	0,00
-4+6	-4.699+3.327	3.954	0,00	0,00
-6+8	-3.327+2.362	2.803	0,00	0,00
-8+10	-2.362+1.651	1.972	0,00	0,00
-10+14	-1.651+1.168	1.389	0,00	0,00
-14+20	-1.168+0.833	0.986	0,00	0,00
-20+28	-0.833+0.589	0.700	3,84	3,84
-28+35	-0.589+0.417	0.495	10,27	14,11
-35+48	-0.417+0.295	0.350	10,20	24,31
-48+65	-0.295+0.208	0.247	17,17	41,47
-65+100	-0.208+0.147	0.174	14,65	56,13
-100+150	-0.147+0.104	0.123	13,32	69,45
-150+200	-0.104+0.074	0.087	7,90	77,35
-200+270	-0.074+0.053	0.062	6,17	83,52
-270+400	-0.053+0.038	0.044	4,73	88,25
-400	-0.038	-0.038	11,75	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9017 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4.699	+4.699	0,00	0,00
-4+6	-4.699+3.327	3.954	0,45	0,45
-6+8	-3.327+2.362	2.803	1,14	1,59
-8+10	-2.362+1.651	1.972	4,46	6,05
-10+14	-1.651+1.168	1.389	5,84	11,89
-14+20	-1.168+0.833	0.986	8,95	20,84
-20+28	-0.833+0.589	0.700	10,02	30,86
-28+35	-0.589+0.417	0.495	23,62	54,48
-35+48	-0.417+0.295	0.350	10,16	64,64
-48+65	-0.295+0.208	0.247	8,31	72,95
-65+100	-0.208+0.147	0.174	3,68	76,63
-100+150	-0.147+0.104	0.123	2,80	79,43
-150+200	-0.104+0.074	0.087	1,95	81,38
-200+270	-0.074+0.053	0.062	1,97	83,36
-270+400	-0.053+0.038	0.044	1,83	85,19
-400	-0.038	-0,038	14,81	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9018 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diámetro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4.699	+4.699	9,12	9,12
-4+6	-4.699+3.327	3.954	8,56	17,68
-6+8	-3.327+2.362	2.803	7,46	25,14
-8+10	-2.362+1.651	1.972	8,27	33,41
-10+14	-1.651+1.168	1.389	12,59	46,00
-14+20	-1.168+0.833	0.986	7,35	53,36
-20+28	-0.833+0.589	0.700	6,00	59,35
-28+35	-0.589+0.417	0.495	7,56	66,92
-35+48	-0.417+0.295	0.350	4,95	71,87
-48+65	-0.295+0.208	0.247	5,56	77,42
-65+100	-0.208+0.147	0.174	3,63	81,05
-100+150	-0.147+0.104	0.123	3,38	84,43
-150+200	-0.104+0.074	0.087	2,30	86,73
-200+270	-0.074+0.053	0.062	2,21	88,94
-270+400	-0.053+0.038	0.044	1,73	90,67
-400	-0.038	-0.038	9,33	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9019

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diámetro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4,699	+4,699	0,17	0,17
-4+6	-4,699+3,327	3,954	4,32	4,49
-6+8	-3,327+2,362	2,803	5,53	10,02
-8+10	-2,362+1,651	1,972	11,76	21,78
-10+14	-1,651+1,168	1,389	9,51	31,29
-14+20	-1,168+0,833	0,986	8,60	39,89
-20+28	-0,833+0,589	0,700	8,16	48,05
-28+35	-0,589+0,417	0,495	10,10	58,15
-35+48	-0,417+0,295	0,350	6,10	64,26
-48+65	-0,295+0,208	0,247	6,36	70,62
-65+100	-0,208+0,147	0,174	4,24	74,86
-100+150	-0,147+0,104	0,123	4,48	79,34
-150+200	-0,104+0,074	0,087	3,21	82,55
-200+270	-0,074+0,053	0,062	3,33	85,87
-270+400	-0,053+0,038	0,044	2,96	88,83
-400	-0,038	-0,038	11,17	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9023

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4,699	+4,699	0,00	0,00
-4+6	-4,699+3,327	3,954	1,16	1,16
-6+8	-3,327+2,362	2,803	2,05	3,20
-8+10	-2,362+1,651	1,972	7,52	10,73
-10+14	-1,651+1,168	1,389	8,37	19,10
-14+20	-1,168+0,833	0,986	10,54	29,64
-20+28	-0,833+0,589	0,700	11,09	40,73
-28+35	-0,589+0,417	0,495	13,87	54,60
-35+48	-0,417+0,295	0,350	7,07	61,67
-48+65	-0,295+0,208	0,247	6,69	68,37
-65+100	-0,208+0,147	0,174	4,92	73,29
-100+150	-0,147+0,104	0,123	5,08	78,37
-150+200	-0,104+0,074	0,087	3,56	81,93
-200+270	-0,074+0,053	0,062	3,45	85,38
-270+400	-0,053+0,038	0,044	2,80	88,18
-400	-0,038	-0,038	11,82	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9024 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4.699	+4.699	5.99	5.99
-4+6	-4.699+3.327	3.954	6.70	12.69
-6+8	-3.327+2.362	2.803	6.38	19.07
-8+10	-2.362+1.651	1.972	9.74	28.81
-10+14	-1.651+1.168	1.389	8.17	36.98
-14+20	-1.168+0.833	0.986	8.38	45.37
-20+28	-0.833+0.589	0.700	8.14	53.51
-28+35	-0.589+0.417	0.495	11.80	65.31
-35+48	-0.417+0.295	0.350	6.15	71.46
-48+65	-0.295+0.208	0.247	6.65	78.10
-65+100	-0.208+0.147	0.174	5.14	83.25
-100+150	-0.147+0.104	0.123	4.46	87.70
-150+200	-0.104+0.074	0.087	2.78	90.48
-200+270	-0.074+0.053	0.062	2.59	93.07
-270+400	-0.053+0.038	0.044	1.83	94.90
-400	-0.038	-0.038	5.10	100.00
TOTAL			100.00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9031 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diametro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4,699	+4,699	0,36	0,36
-4+6	-4,699+3,327	3,954	2,21	2,56
-6+8	-3,327+2,362	2,803	3,48	6,04
-8+10	-2,362+1,651	1,972	10,92	16,97
-10+14	-1,651+1,168	1,389	12,50	29,46
-14+20	-1,168+0,833	0,986	15,23	44,69
-20+28	-0,833+0,589	0,700	11,95	56,64
-28+35	-0,589+0,417	0,495	11,18	67,82
-35+48	-0,417+0,295	0,350	2,60	70,42
-48+65	-0,295+0,208	0,247	2,19	72,61
-65+100	-0,208+0,147	0,174	2,04	74,65
-100+150	-0,147+0,104	0,123	2,63	77,28
-150+200	-0,104+0,074	0,087	2,17	79,44
-200+270	-0,074+0,053	0,062	2,47	81,91
-270+400	-0,053+0,038	0,044	2,21	84,12
-400	-0,038	-0,038	15,88	100,00
TOTAL			100,00	

ANALISIS GRANULOMETRICO

MUESTRA 14-25-AD-JL9033 X

Fracción Granulometrica Mallas Tyler	Fracción Granulometrica mm	Diámetro Medio mm	PESO %	PESO % ACUMULADO %
+4	+4,699	+4,699	12,48	12,48
-4+6	-4,699+3,327	3,954	12,06	24,54
-6+8	-3,327+2,362	2,803	7,27	31,81
-8+10	-2,362+1,651	1,972	12,50	44,31
-10+14	-1,651+1,168	1,389	8,52	52,82
-14+20	-1,168+0,833	0,986	8,53	61,36
-20+28	-0,833+0,589	0,700	6,26	67,62
-28+35	-0,589+0,417	0,495	7,54	75,15
-35+48	-0,417+0,295	0,350	3,08	78,24
-48+65	-0,295+0,208	0,247	3,13	81,37
-65+100	-0,208+0,147	0,174	2,34	83,70
-100+150	-0,147+0,104	0,123	2,55	86,25
-150+200	-0,104+0,074	0,087	1,71	87,97
-200+270	-0,074+0,053	0,062	1,70	89,66
-270+400	-0,053+0,038	0,044	1,22	90,88
-400	-0,038	-0,038	9,12	100,00
TOTAL			100,00	